

AMI-SIL

AMI-SIL CLOTH
STYLE #AS2400
10/08

STYLE: AS2400

NOMINAL WIDTH: 36"

NOMINAL WEIGHT: 24.0 OZ/YD²

NOMINAL THICKNESS: 0.040"

TEMPERATURE RESISTANCE: 1800°F

MELTING POINT: 3000°F

CONTENT: 96% SILICA (MINIMUM)

WEAVE: HERRINGBONE

COUNT: WARP: 30
FILL: 22



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A *WELDING CURTAIN* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3015367.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A ***WELDING CURTAIN*** AND WITH USES AND LIMITATIONS INFORMATION.

NOTE: ABRASION RESISTANT COATING AVAILABLE FOR ADDED DURABILITY. STANDARD COLORS FOR AR COATING ARE BLACK AND ORANGE

ALSO AVAILABLE WITH A HIGH PERFORMANCE PRESSURE SENSITIVE ADHESIVE

ADHESIVE TEMPERATURE RESISTANCE: 300°F

ADHESIVE IS ONLY USED TO AID THE INSTALLATION PROCESS, AFTER THE MATERIAL IS IN PLACE, IT IS USUALLY MECHANICALLY BONDED SO THAT THE ADHESIVE IS NO LONGER NECESSARY.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.