



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

## AMI-FLEX

AMI-FLEX CLOTH  
STYLE# FL2200  
05/06

STYLE #: FL2200

NOMINAL WIDTH: 40" OR 60"

NOMINAL WEIGHT: 22.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.080"

TEMPERATURE RESISTANCE: 600° F

CONTENT: YARNS USED ARE A META-ARAMID/PARA-ARAMID BLEND OUTER LAYER WITH A FIBERGLASS INNER CORE

WEAVE: PLAIN

COUNT: WARP: 20  
FILL: 11

NFPA701/1999  
MEETS THE REQUIREMENTS OF TEST METHOD 1  
TEST REPORTS ON FILE

FL2200-RR & FL2200-DRX HAVE BEEN TESTED BY AN INDEPENDENT LABORATORY IN ACCORDANCE WITH NFPA 1971, SECTION 6-10, 2000 EDITION, THERMAL PROTECTIVE PERFORMANCE, TPP. THIS TEST USES THE STOLL CURVE AS A COMPARISON IN THE GRAPHICAL PRESENTATION.

RAVEL RESISTANCE COATING AVAILABLE - SEE COATINGS SPEC SHEET FOR OPTIONS.

NOTE: COATING FINISHES DECOMPOSE AT TEMPERATURES BELOW THE BASE FABRICS TEMPERATURE RESISTANCE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING.

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 05/06

Date Revised:

Date Reviewed: 09/08

Revision No.: 0

DOCUMENT IS UNCONTROLLED IF PRINTED