



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

AMI-FLEX

AMI-FLEX CLOTH
STYLE# FL2201
01/2010

STYLE #: FL2201

NOMINAL WIDTH: 40" OR 60"

NOMINAL WEIGHT: 22.0 OZ/YD²

NOMINAL THICKNESS: 0.080"

TEMPERATURE RESISTANCE: 600° F

CONTENT: YARNS USED ARE A PREDOMINANTLY ARAMID OUTER LAYER WITH A FIBERGLASS INNER CORE

WEAVE: PLAIN

COUNT: WARP: 20
FILL: 11

FL2201-RR & FL2201-DRX HAVE BEEN TESTED BY AN INDEPENDENT LABORATORY IN ACCORDANCE WITH NFPA 1971, SECTION 6-10, 2000 EDITION, THERMAL PROTECTIVE PERFORMANCE, TPP. THIS TEST USES THE STOLL CURVE AS A COMPARISON IN THE GRAPHICAL PRESENTATION.

RAVEL RESISTANCE COATING AVAILABLE - SEE COATINGS SPEC SHEET FOR OPTIONS.

NOTE: COATING FINISHES DECOMPOSE AT TEMPERATURES BELOW THE BASE FABRICS TEMPERATURE RESISTANCE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 06/09

Date Revised: 01/27/10

Date Reviewed: 01/26/10

Revision No.: 3

DOCUMENT IS UNCONTROLLED IF PRINTED