



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

## VEXTRA

VEXTRA TUBING  
STYLE #GLTV  
01/03

STYLE NO: GLTV

NOMINAL WALL THICKNESS: 0.060"

STANDARD PUT UP: 100 FT/RL

TEMPERATURE RESISTANCE: FABRIC IS RATED AT 1000°F CONTINUOUS, REMAINS STABLE TO 1500°F WITH VERMICULITE COATING.

CONTENT: UNCOATED-100% FIBERGLASS YARNS

WEAVE: PLAIN

INNER DIAMETERS: 3/8", 1/2", 5/8", 3/4", 1", 1-1/4", 1-1/2", 1-3/4", 2", 2-1/4", 2-1/2", 3", 3-1/2"

TUBING FINISH: VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NONCOMBUSTIBLE & ODORLESS COATING.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE MSDS BEFORE HANDLING.

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 01/03

Date Revised:

Date Reviewed: 09/08

Revision No.: 0

DOCUMENT IS UNCONTROLLED IF PRINTED