



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

AMI-FLEX ALUMINIZED

AMI-FLEX CLOTH
STYLE #AFL1200
07/18

MANUFACTURED IN U.S.
FROM IMPORTED and DOMESTIC FIBERS

STYLE NO: AFL1200

NOMINAL WIDTH: 40"

NOMINAL BASE FABRIC WEIGHT: 12.0 OZ/YD²

NOMINAL FINISHED WEIGHT: 14 OZ/YD²

NOMINAL THICKNESS: 0.0385"

BASE CLOTH TEMPERATURE RESISTANCE: 600°F

ALUMINIZED POLYESTER FILM TEMPERATURE RESISTANCE: 450°F

ADHESIVE TEMPERATURE RESISTANCE: 450°F

BASE FABRIC CONTENT: YARNS USED ARE A META-ARAMID/PARA-ARAMID BLEND OUTER LAYER
WITH A FIBERGLASS INNER CORE

BASE FABRIC WEAVE: PLAIN

COUNT: WARP: 20
FILL: 11

FABRIC FINISH: ALUMINIZED POLYESTER FILM ON ONE SIDE

AFL1200 HAS BEEN TESTED TO EN ISO 11612. TEST RESULTS AVAILABLE UPON REQUEST.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

NOTE: WIDTH OF FINISHED PRODUCTS MAY BE NARROWER DUE TO THE LAMINATION PROCESS

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 12/05

Date Revised: 07/26/18

Date Reviewed: 07/26/18

Revision No.: 8

DOCUMENT IS UNCONTROLLED IF PRINTED