



Made in USA of Domestic and/or Imported Materials

PRODUCT DATA SHEET

CARBO-FLEX®– Style No: AFLPN1500

For additional information please contact sales@auburnmfg.com


Description: A composite of a woven fabric, a non-woven material and a layer of aluminized polyester film for reflectivity. The woven fabric is based on yarns made with an aramid outer layer and a fiberglass core. The non-woven is a blend of aramid and carbon (partially carbonized acrylic) fibers.

TECHNICAL DATA	IMPERIAL	METRIC
NOMINAL WIDTH:	40 in 60 in	101.6 cm 152.4 cm
NOMINAL WEIGHT:	17.0 OZ/YD ²	576 g/m ²
NOMINAL THICKNESS:	0.070 in	1.778 mm
NOMINAL BREAKING STRENGTH:	WARP: 200 LBS/IN MIN AVG FILL: 80 LBS/IN MIN AVG	WARP: 350 N/cm FILL: 140 N/cm
TEMPERATURE RESISTANCE:	FIBERGLASS: 1000° F ARAMID: 600°F CARBON: 500°F ADHESIVE: 450°F	FIBERGLASS: 538°C ARAMID: 316°C CARBON: 260°C ADHESIVE: 232°C

STANDARD	TEST	PERFORMANCE LEVEL
EN ISO11612:2015	Molten Metal Splash: Aluminum Iron	D3 E3

PRODUCT HIGHLIGHTS

- ❖ Fabric Finish: Aluminized Polyester film on one side for reflectivity.
- ❖ Width of finished products may be narrower due to the lamination process.
- ❖ Additional Testing: ASTM F955 Molten Metal Iron & Aluminum Impact Test. ASTM F1939 Radiant Protective Performance (RPP).
- ❖ Material should be tested for its suitability in any application. Users should also familiarize themselves with the SDS.



ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY THEMSELVES THAT THE RECOMMENDATIONS ARE SUITABLE FOR THEIR USE AND MEET ALL APPROPRIATE SAFETY & HEALTH STANDARDS.