



Made in USA of Domestic and/or Imported Materials

PRODUCT DATA SHEET

AMI-GLAS® – Style No: AGL3201

For additional information please contact sales@auburnmfg.com

| TECHNICAL DATA | IMPERIAL | METRIC |
|---------------------------------------|------------------------------------------------------|---------------------------------------------------------|
| NOMINAL WIDTH: | 40 in | 101.6 cm |
| NOMINAL BASE FABRIC WEIGHT: | 32.0 OZ/YD ² | 1085 g/m ² |
| NOMINAL FINISHED WEIGHT: | 35.5 OZ/YD ² | 1204 g/m ² |
| NOMINAL THICKNESS: | 0.068 in | 1.727 mm |
| ALUMINUM FOIL THICKNESS: | 0.001 in | 0.025 mm |
| BASE FABRIC COUNT & WEAVE: | WARP: 19 yarns/in FILL: 9 yarns/in PLAIN WEAVE | WARP: 7.5 yarns/cm FILL: 3.5 yarns/cm PLAIN WEAVE |
| BASE CLOTH TEMPERATURE RESISTANCE: | 1000° F | 538° C |
| ALUMINUM FOIL TEMPERATURE RESISTANCE: | 1200° F | 649° C |
| ADHESIVE TEMPERATURE RESISTANCE: | 300° F | 149° C |

PRODUCT HIGHLIGHTS

- ❖ Base Fabric Content: 100% Fiberglass yarns.
- ❖ Width of finished products may be narrower due to the lamination process.
- ❖ Material should be tested for its suitability in any application. Users should also familiarize themselves with the SDS.



ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY THEMSELVES THAT THE RECOMMENDATIONS ARE SUITABLE FOR THEIR USE AND MEET ALL APPROPRIATE SAFETY & HEALTH STANDARDS.