



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

**AMI-SIL**

AMI-SIL CLOTH  
STYLE #CAS4000  
04/18

STYLE: CAS4000

NOMINAL WIDTH: 39", 60"

NOMINAL WEIGHT: 40.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.090"

TEMPERATURE RESISTANCE: 1800°F

MELTING POINT: 3000°F

CONTENT: 96% SILICA (MINIMUM)

WEAVE: PLAIN

COUNT: WARP: 10 FILL: 7



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A *WELDING PAD* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3015367.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A **WELDING PAD** AND WITH USES AND LIMITATIONS INFORMATION.

NOTE: ABRASION RESISTANT COATING AVAILABLE FOR ADDED DURABILITY.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 04/07

Date Revised: 04/18/18

Date Reviewed: 04/18/18

Revision No.: 4

DOCUMENT IS UNCONTROLLED IF PRINTED