



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

## AMI-FLEX

AMI-FLEX CLOTH  
STYLE# FL2200  
7/18

MANUFACTURED IN U.S.  
FROM IMPORTED and DOMESTIC FIBERS

STYLE #: FL2200

NOMINAL WIDTH: 40" OR 60"

NOMINAL WEIGHT: 22.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.080"

TEMPERATURE RESISTANCE: 600°F

CONTENT: YARNS USED ARE A META-ARAMID/PARA-ARAMID BLEND OUTER LAYER WITH A  
FIBERGLASS INNER CORE

WEAVE: PLAIN

COUNT: WARP: 20  
FILL: 11

FL2200-RR & FL2200-DRX HAVE BEEN TESTED BY AN INDEPENDENT LABORATORY IN ACCORDANCE  
WITH NFPA 1971, SECTION 6-10, 2000 EDITION, THERMAL PROTECTIVE PERFORMANCE, TPP. THIS  
TEST USES THE STOLL CURVE AS A COMPARISON IN THE GRAPHICAL PRESENTATION.

FL2200 DRX MEETS THE REQUIREMENTS OF NFPA 701/1999 TEST METHOD SUMMARY 1.  
TEST REPORTS ON FILE.

RAVEL RESISTANCE AND DURABLE RESISTANCE COATINGS AVAILABLE - SEE COATINGS SPEC SHEET  
FOR OPTIONS.

NOTE: COATING FINISHES DECOMPOSE AT TEMPERATURES BELOW THE BASE FABRICS  
TEMPERATURE RESISTANCE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD  
ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

PRODUCTS ARE INTENDED FOR COMMERCIAL USE AND SHOULD NOT BE LAUNDERED

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE  
PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS  
CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY  
HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH  
STANDARDS.

Date of issue: 05/06

Date Revised: 7/26/18

Date Reviewed: 7/26/18

Revision No.: 6

DOCUMENT IS UNCONTROLLED IF PRINTED