

Made in USA of Domestic and/or Imported Materials

PRODUCT DATA SHEET

CARBO-FLEX®– Style No: FLP3000


For additional information please contact sales@auburnmfg.com

Description: 100% preox non-woven combined with a fabric woven from yarns with a meta-aramid/para-aramid blend outer layer and a fiberglass inner layer.

TECHNICAL DATA	IMPERIAL	METRIC
NOMINAL WIDTH:	40 in 60 in	91.4 cm 152.4 cm
NOMINAL WEIGHT:	30.0 OZ/YD ²	1017 g/m ²
NOMINAL THICKNESS:	0.145 in	3.683 mm
NOMINAL BREAKING STRENGTH:	WARP: 200 LBS/IN MIN AVG FILL: 70 LBS/IN MIN AVG	WARP: 350 N/cm FILL: 123 N/cm
TEMPERATURE RESISTANCE:	FIBERGLASS: 1000° F ARAMID: 600° F PREOX: 500° F	FIBERGLASS: 538° C ARAMID: 316° C PREOX: 260° C

PRODUCT HIGHLIGHTS

- ❖ Material should be tested for its suitability in any application. Users should also familiarize themselves with the SDS.



ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY THEMSELVES THAT THE RECOMMENDATIONS ARE SUITABLE FOR THEIR USE AND MEET ALL APPROPRIATE SAFETY & HEALTH STANDARDS.