



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

## VEXTRA

VEXTRA-BLACK  
AMI-FLEX CLOTH  
STYLE #FLVB1700-TP  
01/30/20

Made in USA of Domestic & Imported Materials

STYLE NO: FLVB1700-TP

NOMINAL BASE FABRIC WIDTH: 40" OR 60"

NOMINAL COATED WEIGHT: 20 OZ/YD2

NOMINAL BASE FABRIC THICKNESS: 0.065"

BASE CLOTH: YARNS USED ARE META-ARAMID/PARA-ARAMID BLEND OUTER LAYER WITH A FIBERGLASS INNER CORE

WEAVE: PLAIN

TYPICAL BREAKING STRENGTH: W x F, LBS/IN-300 x 100

TYPICAL TEAR STRENGTH (AVG): W x F, LBS- 55 x 45

COUNT: WARP: 20  
FILL: 11

TEMPERATURE RESISTANCE: BASE FABRIC IS RATED AT 600°F. WITH THE COATING, THE DURABILITY OF THE FABRIC IS ENHANCED.

FABRIC FINISH: VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NONCOMBUSTIBLE & ODORLESS COATING

FABRIC COLOR: BINDERS FOR BLACK PIGMENT ARE SACRIFICIAL AT ELEVATED TEMPERATURES AND MAY BURN OFF WITHOUT AFFECTING THE BASE FABRIC'S TEMPERATURE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

NOTE: WIDTH OF FINISHED PRODUCT MAY BE NARROWER DUE TO SHRINKAGE DURING COATING.

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 02/06

Date Revised: 01/30/20

Date Reviewed: 01/30/20

Revision No.: 4

DOCUMENT IS UNCONTROLLED IF PRINTED