



Made in USA of Domestic and/or Imported Materials


PRODUCT DATA SHEET

VEXTRA®– Style No: FLVB1700-TP

For additional information please contact sales@auburnmfg.com

TECHNICAL DATA	IMPERIAL	METRIC
NOMINAL WIDTH:	40 in 60 in	101.6 cm 152.4 cm
NOMINAL BASE FABRIC WEIGHT:	17 OZ/YD ²	576 g/m ²
NOMINAL COATED WEIGHT:	20.0 OZ/YD ²	678 g/m ²
NOMINAL BASE FABRIC THICKNESS:	0.065 in	1.651 mm
BASE FABRIC COUNT & WEAVE:	WARP: 20 yarns/in FILL: 11 yarns/in PLAIN WEAVE	WARP: 7.9 yarns/cm FILL: 4.3 yarns/cm PLAIN WEAVE
TYPICAL BREAKING STRENGTH:	WARP: 300 LBS/IN FILL: 100 LBS/IN	WARP: 525 N/cm FILL: 175 N/cm
TYPICAL TEAR STRENGTH:	WARP: 55 LBS FILL: 45 LBS	WARP: 245 N FILL: 200 N
BASE FABRIC TEMPERATURE RESISTANCE:	600° F	316° C

PRODUCT HIGHLIGHTS

<ul style="list-style-type: none"> ❖ Content: Yarns are a blend of meta & para-aramid with fiberglass inner core coated with vermiculite. ❖ Coating: Vermiculite. ❖ Color: Black. ❖ Vermiculite is an inorganic, chemically inert, noncombustible & odorless coating which enhances durability of the fabric. ❖ Binders for black pigment are sacrificial at elevated temperatures and may burn off without affecting the base fabric's temperature. ❖ Material should be tested for its suitability in any application. Users should also familiarize themselves with the SDS. ❖ Note: Width of finished product may be narrower due to shrinkage during coating. 	
---	---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY THEMSELVES THAT THE RECOMMENDATIONS ARE SUITABLE FOR THEIR USE AND MEET ALL APPROPRIATE SAFETY & HEALTH STANDARDS.