

Auburn Manufacturing Inc. P.O. Box 220 Mechanic Falls, Maine 04256 U.S.A. 1-800-AMI-6689 • 207-345-8271 FAX: 207-345-3380

Made in USA of Domestic & Imported Materials

## **AMI-GLAS**

AMI-GLAS CLOTH STYLE #GL2401 - 9383 01/17/20

STYLE NO: GL2401 -9383

FABRIC FINISH: HEAT CLEANED NOMINAL WIDTH: 40", 60" OR 72"

NOMINAL WEIGHT: 24.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.055"

TEMPERATURE RESISTANCE: 1000°F

STANDARD COLOR: WHITE, OTHER COLORS AVAILABLE PLEASE CALL FOR DETAILS

CONTENT: 100% FIBERGLASS YARNS

WEAVE: PLAIN

COUNT: WARP: 20

FILL: 11

NOMINAL BREAK STRENGTH: WARP: 200 PPI

FILL: 400 PPI

NFPA701/1999

MEETS THE REQUIREMENTS OF TEST METHOD 1

TEST REPORTS ON FILE

ALL UNCOATED FIBERGLASS YARNS MEET USCG 164.009 "TEST FOR NON COMBUSTIBILITY"

AVAILABLE WITH A HIGH PERFORMANCE PRESSURE SENSITIVE ADHESIVE UP TO 60" WIDE

- ADHESIVE TEMPERATURE RESISTANCE: 300°F
- ADHESIVE IS ONLY USED TO AID THE INSTALLATION PROCESS, AFTER THE MATERIAL IS IN PLACE, IT IS USUALLY MECHANICALLY BONDED SO THAT THE ADHESIVE IS NO LONGER NECESSARY.

RAVEL RESISTANCE COATING AVAILABLE - SEE COATINGS SPEC SHEET FOR OPTIONS.

NOTF: COATING FINISHES DECOMPOSE AT TEMPERATURES BELOW THE BASE FABRICS

TEMPERATURE RESISTANCE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD

ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date Revised: 01/17/20 Date of issue: Date Reviewed: 01/07/20 Revision No