



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

AMI-GLAS

AMI-GLAS CLOTH
STYLE #GL3201
01/17/20

Made in USA of Domestic & Imported Materials

STYLE NO: GL3201

FABRIC FINISH: PLAIN OR 9383 (HEAT CLEANED)

NOMINAL WIDTH: 40", 60", OR 72"

NOMINAL WEIGHT: 32.0 OZ/YD²

NOMINAL THICKNESS: 0.070"

TEMPERATURE RESISTANCE: 1000°F

STANDARD COLOR: WHITE, OTHER COLORS AVAILABLE PLEASE CALL FOR DETAILS

CONTENT: 100% FIBERGLASS YARNS

WEAVE: PLAIN

NOMINAL COUNT: WARP: 19
FILL: 8

NOMINAL BREAK STRENGTH: WARP: 200 PPI
FILL: 400 PPI

ALL UNCOATED FIBERGLASS FABRICS ARE NONCOMBUSTIBLE MEETING USCG 164.009-5(f)

AVAILABLE WITH A HIGH PERFORMANCE PRESSURE SENSITIVE ADHESIVE

- ADHESIVE TEMPERATURE RESISTANCE: 300°F
- ADHESIVE IS ONLY USED TO AID THE INSTALLATION PROCESS, AFTER THE MATERIAL IS IN PLACE, IT IS USUALLY MECHANICALLY BONDED SO THAT THE ADHESIVE IS NO LONGER NECESSARY.

RAVEL RESISTANCE COATING AVAILABLE - SEE COATINGS SPEC SHEET FOR OPTIONS.

NOTE: COATING FINISHES DECOMPOSE AT TEMPERATURES BELOW THE BASE FABRICS TEMPERATURE RESISTANCE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 03/06

Date Revised: 01/17/20

Date Reviewed: 01/07/20

Revision No.: 4

DOCUMENT IS UNCONTROLLED IF PRINTED