



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

VEXTRA

VEXTRA CLOTH
STYLE #GLV2025TP
6/19

FABRIC FINISH: PLAIN OR 9383

NOMINAL BASE FABRIC WIDTH: 40" OR 60"

NOMINAL COATED WEIGHT: 19.3 OZ/YD²

NOMINAL BASE FABRIC THICKNESS: 0.030"

BASE CLOTH: 100% FIBERGLASS YARNS

WEAVE: PLAIN

STANDARD COLORS: BRONZE OR BLACK* OTHER COLORS AVAILABLE PLEASE CALL

COUNT: WARP: 19
FILL: 14



HEAT CLEANED (9383) HAS BEEN TESTED AND FM APPROVED AS A *WELDING CURTAIN* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # RR218770

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A *WELDING CURTAIN* AND WITH USES AND LIMITATIONS INFORMATION.

TEMPERATURE RESISTANCE: FABRIC IS RATED AT 1000°F CONTINUOUS, REMAINS STABLE TO 1500°F WITH VERMICULITE COATING.

FABRIC FINISH: VERMICULITE IS AN INORGANIC, CHEMICALLY INERT, NONCOMBUSTIBLE & ODORLESS COATING

*FABRIC COLOR: BINDERS FOR BLACK PIGMENT ARE SACRIFICIAL AT ELEVATED TEMPERATURES AND MAY BURN OFF WITHOUT AFFECTING THE BASE FABRIC'S TEMPERATURE.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

NOTE: WIDTH OF FINISHED PRODUCT MAY BE NARROWER DUE TO SHRINKAGE DURING COATING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.