

## CARBO-GLAS

CARBO-GLAS CLOTH  
STYLE #PGL2000  
06/15

STYLE NO: PGL2000

DESCRIPTION: 100% CARBON (PARTIALLY CARBONIZED ACRYLIC FIBER) NONWOVEN WITH  
A CORE FABRIC WOVEN FROM 100% FIBERGLASS

COLOR: BLACK

NOMINAL WIDTH: 60"

NOMINAL WEIGHT: 20.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.150"

CONTINUOUS OPERATING TEMPERATURE: 500°F

UPPER TEMPERATURE LIMIT: 1000°F (BASE FIBERGLASS FABRIC)

NOMINAL BREAKING STRENGTH

WARP: 125 POUNDS/INCH

FILL: 50 POUNDS/INCH



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A *WELDING PAD* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3015367.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A **WELDING PAD** AND WITH USES AND LIMITATIONS INFORMATION.

NFPA701/1999  
MEETS THE REQUIREMENTS OF TEST METHOD 1  
TEST REPORTS ON FILE

NRC1.36  
MEETS THE CHEMICAL ACCEPTABILITY OF NRC GUIDE 1.36, FIG. 1  
TEST REPORTS ON FILE

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 04/07

Date Revised: 6/3/15

Date Reviewed: 6/3/15

Revision No.: 3

DOCUMENT IS UNCONTROLLED IF PRINTED