



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

AMI-SIL

SILICONE-COATED
AMI-SIL CLOTH
STYLE #SAS2400-1
04/18

STYLE: SAS2400-1

NOMINAL WIDTHS: 36", 60"

NOMINAL FINISHED FABRIC WEIGHT: 29.0 OZ/YD²

NOMINAL FINISHED FABRIC THICKNESS: 0.047"

BASE FABRIC TEMPERATURE RESISTANCE: 1800°F

COATING TEMPERATURE: 500°F

BASE FABRIC MELTING POINT: 3000°F

CONTENT: 96% SILICA (MINIMUM) CLOTH WITH CURED SILICONE RUBBER ON ONE SIDE

WEAVE: HERRINGBONE

COUNT: WARP: 30
FILL: 22

NFPA 701/2015 – MEETS THE REQUIREMENTS OF TEST METHOD 2. TEST REPORT ON FILE.



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A *WELDING BLANKET* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3015367.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A **WELDING BLANKET** AND WITH USES AND LIMITATIONS INFORMATION.

OTHER: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION, PARTICULARLY FLEXING APPLICATIONS AT ELEVATED TEMPERATURES. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 04/07

Date Revised: 04/18/18

Date Reviewed: 04/18/18

Revision No.: 5

DOCUMENT IS UNCONTROLLED IF PRINTED