

Auburn Manufacturing Inc. P.O. Box 220 Mechanic Falls, Maine 04256 U.S.A. 1-800-AMI-6689 • 207-345-8271 FAX: 207-345-3380

AMI-TUF

STYLE #SGL1700 06/24 Made in the US in Compliance with the BAA.

STYLE NO: SGL1700 NOMINAL WIDTH: 60"

NOMINAL WEIGHT: $17.0 \text{ OZ YD}^2 \pm 10\%$ NOMINAL THICKNESS: 0.016" $\pm 10\%$

BASE FABRIC & WEAVE: FIBERGLASS/SATIN WEAVE (COUNT: WARP: 48; FILL: 31)

STANDARD COLORS & COATING: GRAY, RED & SALMON SILICONE ARE STANDARD, PLEASE CONTACT US

FOR OTHER COLORS.

TEMPERATURE RESISTANCE*: 500° F

NOMINAL BREAKING STRENGTH: WARP: 250 LBS/IN MIN. AVG. FILL: 200 LBS/IN MIN. AVG.

NOMINAL TEAR STRENGTH: FLAME RESISTANCE: (ASTMD6413)

WARP: 50 LBS MIN. AVG. AFTERFLAME: 0 Seconds FILL: 25 LBS MIN. AVG. AFTERGLOW: 0 Seconds

CHAR LENGTH: 1mm x 1mm (Warp & Fill)

NOMINAL BURST STRENGTH: NOMINAL HYDROSTATIC RESISTANCE:

200 LBS/IN² MIN. AVG. 200 LBS/IN² MIN. AVG.

TEST METHOD INFORMATION AVAILABLE - SEE TEST METHOD SUMMARY SHEET

NFPA701/1999
MEETS THE REQUIREMENTS OF TEST METHODS 1 & 2
TEST REPORTS ON FILE



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A *WELDING CURTAIN* TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3015367.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950

INCLUDING DESIGNATION AS A WELDING CURTAIN AND WITH USES AND

LIMITATIONS INFORMATION.

*ALTHOUGH BASE FABRIC IS RATED TO 1000° F CONTINUOUS OPERATING TEMPERATURE, SILICONE COATING IS RATED TO 500° F ON A CONTINUOUS BASIS.

AMI-TUF STYLE SGL1700 IS A FIBERGLASS BASE FABRIC WHICH HAS BEEN COATED WITH OUR SPECIALLY FORMULATED SILICONE RUBBER COMPOUND. IT PROVIDES GREATER ABRASION PUNCTURE AND TEAR RESISTANCE TO OUR BASE FIBERGLASS FABRIC. SILICONE COATED FIBERGLASS FABRIC PROVIDES GREATER LIFE, WATER AND OIL REPELLANCY THAN UNCOATED FABRICS WHILE PROVIDING LOW SMOKE AND FLAME RETARDANCY.

Meets the requirements of ASTM C1695-09. Standard Specification for Fabrication of Flexible Removable and Reusable Insulation for Hot Service

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 04/07 Date Revised: 6/3/2024 Date Reviewed: 6/3/2024 Revision No.: 6