



Auburn Manufacturing Inc.
P.O. Box 220
Mechanic Falls, Maine 04256
U.S.A. 1-800-AMI-6689 • 207-345-8271
FAX: 207-345-3380

AMI-TUF
AMI-TUF CLOTH
STYLE #SGL3200
01/19

NOMINAL WIDTH: 37" OR 60"

NOMINAL WEIGHT: 32.0 OZ YD^2 +/- 10%

NOMINAL THICKNESS: 0.035" +/- 10%

BASE FABRIC & WEAVE: FIBERGLASS/SATIN WEAVE (COUNT: WARP: 47; FILL: 33)

STANDARD COLORS & COATING: GRAY, RED & SALMON SILICONE ARE STANDARD, PLEASE CONTACT US FOR OTHER COLORS.

TEMPERATURE RESISTANCE*: 500° F

NOMINAL TENSILE STRENGTH:
WARP: 500 LBS/IN MIN. AVG.
FILL: 400 LBS/IN MIN. AVG.

NOMINAL BURST STRENGTH
400 LBS/IN^2 MIN.AVG.

NOMINAL TEAR STRENGTH:
WARP: 75 LBS MIN.AVG.
FILL: 50 LBS MIN.AVG.

NOMINAL HYDROSTATIC RESISTANCE
200 LBS/IN^2 MIN.AVG.

TEST METHOD INFORMATION AVAILABLE - SEE TEST METHOD SUMMARY SHEET

NFPA 701/2015 – MEETS THE REQUIREMENTS OF TEST METHOD 2. TEST REPORT ON FILE.

*ALTHOUGH BASE FABRIC IS RATED TO 1000° F CONTINUOUS OPERATING TEMPERATURE, SILICONE COATING IS RATED TO 500° F ON A CONTINUOUS BASIS.

AMI-TUF STYLE SGL3200 IS A FIBERGLASS BASE FABRIC WHICH HAS BEEN COATED WITH OUR SPECIALLY FORMULATED SILICONE RUBBER COMPOUND. IT PROVIDES GREATER ABRASION PUNCTURE AND TEAR RESISTANCE TO OUR BASE FIBERGLASS FABRIC. THIS HEAVY DUTY SILICONE COATED FIBERGLASS FABRIC PROVIDES GREATER LIFE, WATER AND OIL REPELLANCY THAN UNCOATED FABRICS WHILE PROVIDING LOW SMOKE AND FLAME RETARDANCY.



THIS PRODUCT HAS BEEN TESTED AND FM APPROVED AS A WELDING CURTAIN TO ANSI/FM 4950 FOR HOT WORK PROTECTION. TEST DATA AVAILABLE UPON REQUEST. REFERENCE PROJECT ID # 3020654.

SPECIAL MARKINGS: PRODUCT MARKED IN ACCORDANCE WITH FM APPROVAL STANDARD 4950 INCLUDING DESIGNATION AS A WELDING CURTAIN AND WITH USES AND LIMITATIONS INFORMATION.

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING.

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 04/07

Date Revised: 01/03/19

Date Reviewed: 01/02/19

Revision No.: 5

DOCUMENT IS UNCONTROLLED IF PRINTED