



Auburn Manufacturing Inc.  
P.O. Box 220  
Mechanic Falls, Maine 04256  
U.S.A. 1-800-AMI-6689 • 207-345-8271  
FAX: 207-345-3380

**AMI-TUF**

AMI-TUF CLOTH  
STYLE #SGL6300  
09/15

STYLE NO: SGL6300

NOMINAL WIDTH: 36" OR 60"

NOMINAL WEIGHT: 63.0 OZ/YD<sup>2</sup>

NOMINAL THICKNESS: 0.060"

BASE FABRIC & WEAVE: FIBERGLASS/SATIN WEAVE (COUNT: WARP: 43; FILL: 33)

STANDARD COLORS & COATING: GRAY, RED & SALMON SILICONE ARE STANDARD, PLEASE CONTACT US FOR OTHER COLORS.

TEMPERATURE RESISTANCE\*: 500° F

NOMINAL TENSILE STRENGTH:

WARP: 600 LBS/IN MIN. AVG.  
FILL: 500 LBS/IN MIN. AVG.

NOMINAL TEAR STRENGTH:

WARP: 200 LBS MIN.AVG.  
FILL: 150 LBS MIN.AVG.

\*ALTHOUGH BASE FABRIC IS RATED TO 1000° F CONTINUOUS OPERATING TEMPERATURE, SILICONE COATING IS RATED TO 500° F ON A CONTINUOUS BASIS.

AMI-TUF STYLE SGL6300 IS A FIBERGLASS BASE FABRIC WHICH HAS BEEN COATED WITH OUR SPECIALLY FORMULATED SILICONE RUBBER COMPOUND. THIS HEAVY DUTY SILICONE COATED FIBERGLASS FABRIC PROVIDES GREATER LIFE, WATER AND OIL REPELLANCY THAN UNCOATED FABRICS WHILE PROVIDING LOW SMOKE AND FLAME RETARDANCY.

NOTE: MATERIAL SHOULD BE TESTED FOR ITS SUITABILITY IN ANY APPLICATION. USERS SHOULD ALSO FAMILIARIZE THEMSELVES WITH THE SDS BEFORE HANDLING

---

ALL STATEMENTS HEREIN ARE EXPRESSIONS OF OPINION WHICH WE BELIEVE TO BE ACCURATE AND RELIABLE BUT ARE PRESENTED WITHOUT GUARANTEE OR RESPONSIBILITY ON OUR PART. ANYONE INTENDING TO USE RECOMMENDATIONS CONTAINED IN THIS PUBLICATION CONCERNING EQUIPMENT, PROCESSING TECHNIQUES OR PRODUCTS SHOULD FIRST SATISFY HIMSELF THAT THE RECOMMENDATIONS ARE SUITABLE FOR HIS USE AND MEET ALL APPROPRIATE SAFETY AND HEALTH STANDARDS.

Date of issue: 08/21/15

Date Revised: 9/16/15

Date Reviewed: 9/15/15

Revision No.: 1

DOCUMENT IS UNCONTROLLED IF PRINTED